



Now manufactured by:

Solid Products, Inc.

*Over 30 years of manufacturing premier
drywall finishing products.*

Richfield, WI 53076

1-800-344-8861

NEW

Sudden Bond™

FAST5™

Sprayable Drywall Surfer

FAST5 Sprayable Drywall Surfer gives a Level 5 Gypsum Board Finish, as described in GA-214 and ASTM C840.

Advantages:

- Reduces labor, faster than skim coating with joint compound.
- Easier to paint.
- More resistant to abuse damage.
- Conceals most sanding fuzz.
- Competitively priced.
- Cleans up with soapy water.

FAST5 is applied with an airless spray machine, over a Level 4 Gypsum Board Finish.

FAST5 may be sanded to remove small imperfections, overspray, or to yield a smoother surface.

Call Today for Pricing

Sudden Bond™

FAST5

Product Name:

Sudden Bond FAST5 Drywall Surfer

Manufacturer:

Solid Products, Inc.
3290 Industrial Rd.
Richfield, WI 53076
Phone (262)628-3840
(800)344-8861
Fax (262)628-4068

Product Description:

FAST5 Drywall Surfer gives a Level 5 Gypsum Board Finish, as described in GA-214 and ASTM C840.

FAST5 Drywall Surfer reduces labor and requires less time than a skim coat of joint compound. **FAST5** produces a finish that is easier to paint than a skim coat of joint compound. Also the surface is more resistant to abuse damage than a skim coat of joint compound. Unlike drywall primers, **FAST5** conceals most sanding fuzz.

Packaging: Available in 5 gallon pails.

Colors: Available in one color – White.

Preparation:

1. Finish all drywall to a Level 4 Gypsum Board Finish as described in GA-214 and ASTM C840.
2. Fix all paper tears and blisters.
3. Keep sanding to a minimum.
4. Mask surfaces that will not need to be covered with **FAST5**.
5. Brush drywall surfaces to remove any excess sanding dust.
6. Sweep floors to prevent dust and debris from being blown onto the **FAST5** surface by the airless sprayer.

Application Equipment:

Apply **FAST5** Drywall Surfer with an airless spray machine equipped with a .621 to .631 spray tip. Use, as a minimum, 3/8" I.D. material line. Material pressure should be limited to 3000 psig at the machine. Minimum pump capacity: 1.0 gpm.

FAST5 may be sanded to remove small imperfections, overspray, or to yield a smoother surface.

Over a Level 4 Gypsum Board Finish spray apply a 14 mil coat of **FAST5** Drywall Surfer.

Use NIOSH approved N95 particle Respirator (dust mask).

Coverage:

Coverage will vary according to surface porosity, and equipment.

Average Coverage: 75-100 sq. ft./gal.

Mixing and Cleaning:

Stir material thoroughly. **Do Not Thin FAST5**. Thinning depletes the hardness and coverage qualities of the product and nullifies the warranty.

Clean tools, equipment, and skin with soapy water and rinse.